

Grease Compatibility Chart — Thickener Mixing, NLGI Grades and Changeover Procedure

cBallast Technical Sourcing · Lubricating greases · issued 2026-10-04 · cballast.com/documents/grease-compatibility-chart

Which grease thickeners can be mixed and which must never meet, the NLGI consistency scale, base-oil compatibility, and the safe purge procedure when changing grease type in a bearing.

Thickener compatibility matrix

| Li | Li-complex | Ca-sulfonate | Polyurea | Clay (bentone) | Al-complex |

Lithium | — | C | C | I | I | I | I |

Lithium-complex | C | — | C | B | I | C |

Calcium-sulfonate | C | C | — | B | I | B |

Polyurea | I | B | B | — | I | I |

Clay (bentone) | I | I | I | I | I | — | I |

Aluminium-complex | I | C | B | I | I | — |

C = generally compatible · B = borderline, test or purge thoroughly · I = incompatible: the mixture softens or hardens and loses its oil. Matrices differ slightly between producers because additive packages matter as much as thickeners — when in doubt, treat the pair as incompatible. Base oils add a second layer: mineral and PAO mix; silicone and PFPE oils mix with nothing else.

NLGI consistency grades

NLGI | Worked penetration (0.1 mm) | Feel | Typical duty |

0 | 355–385 | semi-fluid | Central systems, gear couplings |

1 | 310–340 | very soft | Low temperature, high water wash |

2 | 265–295 | standard | The default bearing grease (e.g. SKF LGMT 2) |

3 | 220–250 | firm | Vertical shafts, high ambient |

Changing grease type safely

Same thickener and base oil? Top up normally.

Compatible pair (C): relubricate at half the usual interval twice, so the old grease is progressively displaced.

Borderline or incompatible (B/I): purge — grease through the bearing until fresh grease exits clean, or strip and wash the bearing and housing with solvent, dry, and repack 30–50 % free volume. Mark the housing with the new grease type.

Polyurea-filled electric-motor bearings deserve special care: most general lithium EP greases are incompatible with them — purge fully or replace the sealed bearing.

High-viscosity and special greases (e.g. SKF LGEM 2 for slow heavily-loaded bearings) follow the same matrix by their thickener family — the designation letter rarely says which, so check the datasheet line "thickener". Relubrication quantities and intervals per bearing size are in the bearing maker's tables; bearing dimensions themselves are in the bearing chart.

Frequently asked questions

Can I mix lithium and polyurea grease? No — lithium and conventional polyurea thickeners are incompatible: the blend softens and bleeds oil. Purge the bearing completely before changing between them. What does NLGI 2 mean? The standard consistency grade for rolling-bearing grease: worked penetration 265–295 tenths of a millimetre — firm enough to stay in the bearing, soft enough to flow to the contacts. Are lithium and lithium-complex greases compatible? Yes, generally — they share the thickener chemistry; follow the shortened-interval top-up routine so the old fill is displaced. How do I change to an incompatible grease? Purge the bearing until only fresh grease exits, or dismantle, wash and dry the bearing and housing, then repack 30–50 % of the free volume with the new grease and label the point. Do base oils affect compatibility too? Yes: mineral and PAO base oils mix, but silicone and PFPE-based greases are incompatible with everything outside their own family regardless of thickener.

Part numbers and designations are those of the original manufacturers and are given for identification. cBallast is an independent supplier. © cBallast 2026 · cballast.com