

CONTENT

AIR & WATER

AIR CONDITION

BRAKE

BREATHING

BUNKER

CHEMICAL

COOLANT

FOOD

FUEL

GAS

HYDRAULIC

MATERIAL HANDLING

OIL

OIL COOLING

POWERSTEERING

PVC

STEAM

WELDING & GAS

INDEX

Codan 2601 Gas Hose



Codan 2601 - EN ISO 3821 / EN 559: 2003

Flexible, smooth, orange hose for liquefied petroleum gas (LPG), propane/butane, to EN ISO 3821/EN559.

In accordance with the new EN ISO 3821 and EN559, the hose is primarily for use in industrial welding and cutting applications. The 6.3 mm and 11.0 mm hoses are DG approved. Please contact Codan for further information.

Type nr. 2601

Application: LPG / Propane / Butane

Standard Length: 50 metres

Working Temperature: -30°C to 80°C

Inside: NBR

Colour: Black

Reinforcement: Ester

Outside: EPDM

Colour: Orange

Standards: EN ISO 3821 / EN 559: 2003

Inside dia. (mm)	Outside dia. (mm)	Working Pressure BAR	Burst Pressure BAR	Bend Radius (mm)	Weight (g/m)	Product code
4,0	11,0	20	60	35	110	2601004000
5,0	11,4	20	60	40	116	2601005000
6,3	13,3	20	60	40	141	2601006000
8,0	15,0	20	60	40	173	2601008000
9,0	16,0	20	60	115	188	2601009000
10,0	17,0	20	60	50	203	2601010000
11,0	18,0	20	60	55	221	2601011000

This hose specification sheet has been prepared with great care in order to provide you with all the information you need. Written advice must be obtained from Codan Rubber before using any hose with untested media or before using in applications not covered in the product data sheet. Codan Rubber recommends regular maintenance, care and inspection of hoses before use. Hoses should be replaced if any physical damage is seen, especially to the cover of the hose or in the area around the couplings. All products must be stored in accordance with ISO 2230:2002 (Storage of vulcanised Rubber Products).

The individual conditions of an application will affect the life time of each product. Therefore please ensure that resistance to chemicals and cleaning procedures in our written product information is complied with. Codan Rubber's warranty is void in the event of misuse such as excessive bending, crushing, stretching, use with incorrect media or use in environments outside the hose specification.

Please contact Codan Rubber for individual product manufacturing tolerances.