

FLOWCONCEPT

Item No. **Braided Hose**

Ester base - TPU

Technical Data

Properties	Method	Value	Note
Hardness	DIN 53505	85 Shore A	
Specific Gravity	DIN 53479	1.2g/cm	
Tensile Strength	DIN 53504	40N/mm	
Ultimate Elongation	DIN 53504	450%	
Abrasion Loss	DIN 53516	30mm	
Rebound Resilience	DIN 53512	42%	
Tear Strength	DIN 53515	70kN/m	
Burst Pressure		64 bars	

** Working temperature from- 20 C to 80 C

** Standard Burst Pressure of 10x14.5 and 13x18 are 56 bars.

** All data are approximate and correct to the best of our knowledge and are not guaranteed.

** Conversion of burst pressure to working pressure is 4:1 or 2.5 : 1 depending on your own cc

company